Medium

Typical values

Property	Unit	Method							
Grammage	**g/m²**	**ISO 536**	**100**	**105**	**110**	**115**	**120**	**125**	**150**
Moisture average	%	Online	8,0	8,0	8,0	8,0	8,0	8,0	8,0
CMT 30	N	ISO 7263	165	170	175	185	190	195	250
SCT CD	kN/m	ISO 9895	1,75	1,80	1,85	2,00	2,05	2,10	2,60
SCT MD	kN/m	ISO 9895	2,70	2,80	#	#	#	#	#
Tensile strength MD	kN/m	ISO 1924-3	4,9	5,1	#	#	#	#	#
Tensile strength CD	kN/m	ISO 1924-3	1,8	1,9	#	#	#	#	#
Porosity, Gurley	sec	ISO 5636-5	30	35	#	#	#	#	#

Guaranteed values

Property	Unit	Method							
Grammage	**g/m²**	**ISO 536**	**100**	**105**	**110**	**115**	**120**	**125**	**150**
Grammage average, min/max	%	ISO 536	+/-3	+/-3	+/-3	+/-3	+/-3	+/-3	+/-3
Moisture average	%	Online	8,0 +/-1	8,0 +/-1	8,0 +/-1	8,0 +/-1	8,0 +/-1	8,0 +/-1	8,0 +/-1
CMT 30, min.	N	ISO 7263	155	160	165	170	175	180	230
SCT CD, min	kN/m	ISO 9895	1,55	1,65	1,70	1,80	1,85	1,90	2,30

Typical values — Typical is what a customer can expect to receive on a customer reel average
Guaranteed values — Guaranteed is a min/max value of a property on a customer reel average
Test conditions — 50% RH and 23°C

Internal code — 6000

Issue date — March 2017

Latest updated version to be found on www.dssmith.com/paper

PROTECTION
DESIGN
IMAGE